OCT 21, 2019

🌐 Aptamer 1-step conjugation protocol

Jorge Fernandez Mendez¹

¹Universidad Complutense de Madrid

AEGIS - Madrid iGEM 2019

Jorge Fernandez Mendez

Universidad Complutense de Madrid

ABSTRACT

Adaptated version of the crosslinking bioconjugation protocol depicted in <https://doi.org/10.1177/1087057106292138> publication.

The following protocol depicts the steps to follow for proper crosslinking of amino modified DNA aptamers with carboxyl surface functionalized latex beads..

MATERIALS

MATERIALS

⊗ 500mg Sulfo NHS (N-Hydroxysulfosuccinimide) **G-Biosciences Catalog #BC9**

⊗ EDC N-(3-Dimethylaminopropyl)-N'-ethylcarbodiimide **Sigma – Aldrich Catalog #39391-10ML**

- PBS Buffer pH =7.4
- PBS-T Buffer (Tween-20 0.01 %) pH=7.4
- MES Buffer 50 mM pH= 5.9
- Glycine 50 mM aqueous solution
- 5' Amino-terminal modified capture aptamer, resuspended in distilled water at 100 µM concentration.

- 100-1000 µL Micropipette
- 2-20 Micropipette
- 1000 µL Micropipette tips
- 200 µL Micropipette tips
- Eppendorf Tubes (1.5 mL)
- Thermoblock
- Microfugue
- Ice

OPEN ACCESS

DOI:
dx.doi.org/10.17504/protocols.io.8h4ht8w

Protocol Citation: Jorge Fernandez Mendez 2019. Aptamer 1-step conjugation protocol. **protocols.io** <https://dx.doi.org/10.17504/protocols.io.8h4ht8w>

License: This is an open access protocol distributed under the terms of the [Creative Commons Attribution License](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited

Protocol status: Working
We use this protocol and it's working

Created: Oct 20, 2019

Last Modified: Oct 21, 2019

PROTOCOL integer ID:
28956

Reactive Preparations

- 1 Prepare a 0.4 M aqueous solution of sulfo-NHS. Weight 44.5 mg of sulfo-NHS and dissolve it in

500 μL of distilled water. Keep stored at 4 °C. Sulfo-NHS can be stored under refrigerator for a couple of months.

- 2 Prepare 0.32 M EDC solution. Pipette 29.5 μL of 97% EDC in 470.5 μL of distilled water. EDC solutions must be stored at -20 °C.

It's convenient to prepare freshly EDC solutions for assuring proper conjugation, unless it will be used within the following days consecutively.

- 3 Reconstitute the aptamers by pipetting 30 μL of 100 μM stock on an empty eppendorf tube. Place in a thermoblock at 95 °C for 10 minutes. And move the tube quickly to an ice bath, letting them to cool down for 10 minutes more. The reconstituted aptamer can be kept at 4°C for several weeks, or store freezed at -20 °C for long periods.

Latex beads preparation

- 4 Dilute 200 μL of 2.5 % wt beads stock with 300 μL of additional MES buffer. Reaching a final volume of 500 μL .

- 5 15000 rpm , 4 minutes the tube at 15.000 rpm for 4minutes. Discard the supernatant and resuspend them in 500 μL of MES buffer.

For beads resuspension, repeated pipetting it's highly recommended, aspirating and blowing out in the eppendorf tube. It's crucial assuring perfect beads disperssion, if little aggregates are appreciated, try reducing centrifugation times or sonicating the beads for resuspension (5 minutes sonication at moderate power).

Latex beads Conjugation

- 6 Mix on an eppendorf tube 40 μL of sulfo-NHS 0.4 M , 40 μL of 5' amino terminal modified aptamer and 40 μL of 0.32 M EDC solution.
- 7 Vortex for 20 seconds the prepared 500 μL latex bead suspension in MES and add quickly 160 μL of the conjugation solution prepared in step 6.

- 8 Cover with aluminium foil or tape the eppendorf tube, and Incubate the prepared solution for 1h 30 minutes at room temperature with strong agitation. (250 rpm on a thermoblock agitator is recommended).
- 9 Add 100 µL of 50 mM glycine solution. Let the beads incubate for 10 minutes more under agitation. The glycine will react with any of the remaining activated crosslinking groups.

Latex beads Washings

- 10 15000 rpm , 4 minutes the tubeCentrifugate the beads at 15.000 rpm for 4 minutes, discard the supernatant and resuspend the pellet in 500 µL of PBS-T.

Repeat that washing step for three times.

- 11 Beads can be resuspended in the desired buffer. PBS-T 0.05 % (Tween-20) guarantee adequate beads disperssability in nitrocellulose membranes.

Conjugated beads can be stored at 4°C for several weeks.