VERSION 2

OCT 17, 2019

OPEN ACCESS

DOI:
dx.doi.org/10.17504/protocols.io.8cehste

External link:
<https://2019.igem.org/Team:EPFL/Microneedles>

Protocol Citation: Stephania Konstantinidi, Hana Samet 2019. Fabrication of Microneedle Patches.

protocols.io
<https://dx.doi.org/10.17504/protocols.io.8cehste>

License: This is an open access protocol distributed under the terms of the [Creative Commons Attribution License](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited

Protocol status: Working
 We use this protocol and it's working

Created: Oct 17, 2019

Last Modified: Oct 17, 2019

🌐 Fabrication of Microneedle Patches V.2

Stephania Konstantinidi¹, Hana Samet¹

¹EPFL - EPF Lausanne

iGEM EPFL

Dana Mozaffari

ABSTRACT

The goal is to create a microneedle. patch, which, by applying it on a leaf, will extract amplification-ready DNA.

All MN patches used for DNA extraction were fabricated using polydimethylsiloxane molds. These molds were fabricated by laser ablation, and the dimension of each mold is approximately 10 mm × 10 mm, which has 15 × 15 arrays of microneedle conical cavities. The height of each cavity is 800 μm, and the diameters of the tip and base are 10 and 300 μm, respectively.

Keywords: Microneedles

Mold preparation

- 1 Clean the polydimethylsiloxane molds.
 - 1.1 Heat deionised water to 100 degrees Celsius 100 °C using a becher.
 - 1.2 Put the mold(s) into the water and stir softly.
 - 1.3 Remove the molds and let them dry in a chemical hood for 1-2 hours.

A solutionPVA SPVA SolutionP

- 2 Prepare the PVA solution
 - 2.1 Heat 28g of deionised water to 110 degrees Celsius 110 °C .
 - 2.2 Add 4g of poly(vinyl alcohol) (30– 70 kDa, 10 wt %) powder and stir until transparent.

Microneedle Fabrication

3 Fabricate the Microneedles

- 3.1 Stick the molds on the bottom of an adequate recipient using double-sided tape.
- 3.2 Add 1.5 mL of PVA solution on top of the mold.
- 3.3 Centrifuge at 4000 rpm for 20 minutes at 40 degrees Celsius.
- 3.4 Let the microneedles dry under a chemical hood overnight.
- 3.5 Remove the microneedles from the molds.

Use Microneedles !

4 The microneedles are ready for use.