APR 23, 2021

UH-PAM Protocol

Seonggun Joe¹, Massimo Totaro¹, Hongbo Wang¹, Lucia Beccai¹¹Istituto Italiano di Tecnologia (IIT)

Seonggun Joe

ABSTRACT

The protocol outlines the fabrication process of UH-PAM, and it prompts you with the details to repeat and reproduce our works.

BEFORE START INSTRUCTIONS

1. Use AutoCAD/SolidWorks/CATIA to modify the attached files.
2. For further information, please contact us as follow:
seonggun.joe@iit.it
lucia.beccai@iit.it

OPEN ACCESS

DOI:

dx.doi.org/10.17504/protocols.io.bi8bkhsn

External link:

<https://doi.org/10.1371/journal.pone.0250325>

Protocol Citation: Seonggun Joe, Massimo Totaro, Hongbo Wang, Lucia Beccai 2021. UH-PAM Protocol. **protocols.io** <https://dx.doi.org/10.17504/protocols.io.bi8bkhsn>

MANUSCRIPT CITATION:

Joe S, Totaro M, Wang H, Beccai L (2021) Development of the Ultralight Hybrid Pneumatic Artificial Muscle: Modelling and optimization. PLoS ONE 16(4): e0250325. doi: [10.1371/journal.pone.0250325](https://doi.org/10.1371/journal.pone.0250325)

License: This is an open access protocol distributed under the terms of the [Creative Commons Attribution License](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited

Protocol status: Working

Created: Jul 31, 2020

PROTOCOL integer ID:
39907

- 1 Please download and unzip "UH-PAM Protocol.zip" in the attached file.

- 2 Cut a commercial polyurethane open-cell foam and Plexigals as attached files (UH-PAM_2D Layers.dwg)

We recommend 2D laser cutter (Versa LASER VLS 3.5), in order to properly cut them.
For the print parameters, please follow the table, as below:

	POWER	SPEED	PPI	Z-axis
Segment foam	60%	30%	1,000	12.6 mm
Bridge foam	60%	30%	1,000	6.4m m
Flexiglas rings	100%	10%	1,000	1mm

- 3 Print the molds (in the attached files, Mold(1) to (4).stl) by using a 3D printer.
- 4 Pour the mixed liquid into mold (1) and (3), and assemble it with mold (2) and (4), respectively.
- 5 After curing for 15 hours, detach the skins from the molds
- 6 Bond the segment foam with the bridge foam, and build a foam structure.
Here, do not pour the silicone and use a silicone adhesive material (SIL-Poxy® adhesive, Smooth-

On Inc).

Otherwise, the foam absorbs the silicone, and its mechanical property would be changed.

7 Bond all skin parts and the foam structure, by brushing the Dragonskin 30.

8 After curing the silicone, bond both halves of the skin.